TEST REPORT

LAB LOCATION:TURKEY
LAB NO. : (7216)288-0181
SERVICE TYPE: Regular
DATE IN: October 14th , 2016
DATE OUT: November 01st , 2016

MATERIAL SUBMITTED	:	ALPHA ACOUSTIKI LTD. (Attn: teo@vibro.gr)
SUPPLIER REFERENCE	:	ISOLFON SEP & POLYFON
BUYER	:	/
MANUFACTURER	:	/
COUNTRY OF ORIGIN	:	TURKEY
COUNTRY OF DESTINATION	:	GREECE
SAMPLE DESCRIPTION	:	**Sample A:** PU FOAM
COLOR	:	/
SUBMITTED CARE INSTRUCTION	:	/
GENERAL CONCLUSION	:	PASS

SUMMARY OF TEST RESULTS

TEST REQUIRED	Sample A
FMVSS 302:1991 Flammability of interior materials	PASS

P:PASS
F:FAIL

EXECUTIVE SUMMARY: Only vendor selected tests have been performed and submitted samples have been rated as "PASS".

Remark 1: "FMVSS 302:1991 Flammability of interior materials" test has been performed by BV UK Laboratories as subcontracted [Report No: TR909/1833141]

Bureau Veritas Consumer Products Services Turkey
BV CPS Test Lab. Ltd. Sti.

Eylem Yaldızlı
Program Manager -Hardline

Ozlem Dogan
Client Group Manager

BV CPS TEST LABORATUVARLARI LTD. STI.
BUREAU VERITAS CONSUMER PRODUCTS SERVICES
Yalçın Koreş Caddesi No:22 Erdinç Binaları A Blok
2. Kule 1. Kat 34209 Güneşli, Istanbul / Turkey
Tel:+90.212.494 35 35 Fax:+90.212.494 35 60
email:info.turkey@bvcps.com.tr
website: www.bureauveritas.com/cps

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at www.bureauveritas.com/cps and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted.
Our report includes all the tests requested by you and the results thereof based upon the information that you provided to us. You have 60 days from the date of issuance of this report to notify us of any material error or omission caused by our negligence, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents

-Photo of the Submitted Sample-

Sample A


BUREAU VERITAS

TEST RESULTS

Specifications: FMVSS 302:1991 – Flammability of interior materials.

Test Details

Application time:	15 Seconds
Conditioning:	21 ± 5°C / 50% ± 10% RH, ≥24hrs
Gas used:	Natural

Item Description: Foam
Color: Dark Grey

Specimen Results:

Test Criteria	1	2	3	4
Direction of test	↑	↓	↑	↓
Thickness value of sample	15.1	14.9	15.3	15.0
(Max/Min.) (mm)	15.0	14.8	15.1	14.9
Did specimen ignite?	NO	NO	NO	NO
Separation of flaming debris	NO	NO	NO	NO
Did specimen self-extinguished?	-	-	-	-
Burnt distance in (Inch)	0.00	0.00	0.00	0.00
Time in seconds to burnt distance	0.0	0.0	0.0	0.0
Result	**PASS**	**PASS**	**PASS**	**PASS**

Pass/Fail Criteria:

Material shall not burn, nor transmit a flame front across its surface at a rate of more than 4 inches per minute. However, the requirement concerning transmission of a flame front shall not comply with a surface created by cutting of a test specimen for purpose testing.

If a material stops burning before it has burned for 1 minute from the start of timing, and has not burned more than 2 inches from the point where timing was started, it shall be considered to meet the burn rate requirement in the standard.

- END OF REPORT -